



	QUERSCHN. cm ² /m	GEWICHT JE MATTE	STAB- ABSTAND	STAB- Ø	LÄNGE BREITE
Baustahlmatten					
					
Q188	1,88	41,776	150	6,0	6000
	1,88		150	6,0	2300
Q257	2,57	56,776	150	7,0	6000
	2,57		150	7,0	2300
Q335	3,35	74,260	150	8,0	6000
	3,35		150	8,0	2300
Q424	4,24	83,873	150	9,0	6000
	4,24		120	8,0	2300
Q524	5,24	100,876	150	10,0	6000
	5,24		150	10,0	2300
Q636	6,36	132	100	9,0	6000
	6,36		125	10,0	2350
R188	1,88	33,6	150	6,0	6000
	1,13		250	6,0	2300
R257	2,57	41,2	150	7,0	6000
	1,13		250	6,0	2300
R335	3,35	50,2	150	8,0	6000
	1,13		250	6,0	2300
R 424	4,24	67,2	150	9,0	6000
	2,01		250	8,0	2300
R 524	5,24	75,7	150	10,0	6000
	2,01		250	8,0	2300

Ø	kg/m
Betonstahl	
	
6	0,222
8	0,395
10	0,617
12	0,888
14	1,21
16	1,58
20	2,42
25	3,85
28	4,83
32	6,31
40	9,86